

Product description

Grade:

Vicell® 6703/80 DS

PROPERTY	EDANA METHODE	TOLERANCES			UNIT
		Min	Target	Max	
Basis weight	WSP 130.1	76	80	84	g/m ²
Thickness 1-ply	WSP 120.6	1	1,05	1,10	mm
Thickness 1 -ply after winder	WSP 120.6	0,9	0,95	1,00	mm
MD Tensile strength dry	Option B WSP 110.4	20,50	24,5	29,50	N/5cm
CD		-	17,0	-	N/5cm
MD Elongation dry	Option B WSP 110.4	-	10,00	-	%
CD		-	12,00	-	%
MD Tensile strength wet	Option B WSP 110.4	8,00	10,00	12,00	N/5cm
CD		-	6,50	-	N/5cm
Liquid Absorbency	WSP 10.01	7,8	8,50	11	g/g
Capacity		624	680	880	g/m ²
Liquid strike through time	WSP 70.3	-	2	4	s

This is not a specification.

Properties are given as typical average values off-machine with tolerances of +/-3 sigma.